COMPANY PROFILE

A Leader in High-Grade Seamless Steel Tubular Products

Titanium Welded Tube

Stainless Steel Tube

-
-
- Clean pipe
-
-

Steel Chofu Seamless
 가 Uginе Sejournett
 1956 가 ,
 1980

Stainless Steel Tube	2
Precision Tube	6
Specialty Tube	7
Titanium Welded Tube	8
Quality Control and Inspection System	9
Material Grades	10
Standard Manufacturing Range	18
Company Profile	20

Seamless Tube

Stainless Steel Tubes and Pipe	Piping use for nuclear power plants, Chemical industry, Petrochemical industry, etc. (, ,) Heat exchanger use for power plants, Petrochemical industry, etc. Mother tubes for redrawing Industrial machinery use (, ,)
Precision Tube	Fuel Cladding Tubes for FBR, Control rods for PWR, Tapered tubes for rocket engines, Clean pipe for the semiconductor industry (, , ,)
Specialty Tube	Wrapper tubes for FBR, Torque tubes for aircraft, Electro-polished pipe (,)
Titanium Welded Tube	Condenser tubes for thermal and nuclear (,) power plants, Tubes for desalination plants

Production Process of Seamless Stainless Steel Tubes and Pipe

Kobe Special Tube's seamless stainless tubes and pipe are made with a variety of sophisticated equipment. Our high-quality ingots are produced utilizing electric arc melting and vacuum-oxygen decarburization (VOD). Our vacuum induction melting process (VIM), electroslag remelting process (ESR), and vacuum arc remelting process (VAR) are applicable for special use. These ingots are rolled or forged into blooms that are then further processed using the Uginé Sejourmet hot extrusion process and turned into high-quality seamless stainless tubes and pipe. Small-diameter and precision tubes and pipe are manufactured by a drawing and reducing process and extra-long tubes up to 36m by long-tubing facilities.

Vacuum oxygen decarburization process(VOD)

Shipment

Long-tubing facilities

Through-type annealing furnace 2,000 ton extrusion press

Stainless Steel Tube

Seamless Stainless Steel Tubes and Pipe

Stainless Steel Tube

Widely Applicable Seamless Stainless Steel Tubes and Pipe

Seamless stainless steel

/ feedwater heater (36m)

Stamicabon Snamprogetti 가 ,

()

가 , , Austenitic, ferritic

U-shaped heat exchanger tubes

Petrochemical plant

Stainless steel pipe

Urea fertilizer plant

Nuclear power plant

Precision Tube

Esteemed for High Technology Precision Tube

가

1987

Stainless steel fuel cladding tubes for fast breeder reactors

Work space for precision tube

Specialty Tube

Challenging the Future Specialty Tube

MONJU
 Tube) creep Swell , 가 TP316 (Seamless 1987

Steel belt

Torque tubes

Wrapper tube with pad

Low-finned tubes

Titanium Welded Tube

Efficient Tube for an Advanced New Age Titanium Welded Tube

Titanium Welded Tube

Efficient Tube for an Advanced New Age

Titanium Welded Tube

Kobe

가

Quality Control and Inspection System

Quality Control

Kobe

Chofu-Kita
ISO9002, JIS, LR, NV, TUV

Corrosion testing equipment

Combined ultrasonic and eddy current tester

100 ton tensile test machine

Setouchi
Chofu-Kita

Material Grades

Ferritic Stainless Steel Tubes and Pipe

Code	Material Grade	Chemical Composition (%)								
		C,max	Si,max	Mn,max	P,max	S,max	Ni	Cr	Mo	Cu
403	13Cr -LSi	0.15	0.50	1.00	0.040	0.030	0.50	11.50~13.00		
405	13Cr -0.2Al	0.08	1.00	1.00	0.040	0.030	0.50	11.50~14.50		
409	11Cr -Ti	0.08	1.00	1.00	0.040	0.030	0.50	10.50~11.75		
409L	LC-11Cr -Ti	0.03	1.00	1.00	0.040	0.030	0.50	10.50~11.75		
410	13Cr	0.15	0.75	1.00	0.040	0.030	0.50	11.50~13.50		
410Ti	13Cr -Ti	0.08	1.00	1.00	0.040	0.030	0.50	11.50~13.50		
430	17Cr	0.12	0.75	1.00	0.040	0.030	0.50	16.00~18.00		
430Ti	17Cr -Ti	0.10	1.00	1.00	0.040	0.030	0.75	16.00~18.00		
436L	18Cr -1Mo-Ti	0.025	1.00	1.00	0.040	0.030	0.50	16.00~19.00	0.75~1.25	
XM-8	18Cr -Ti	0.07	1.00	1.00	0.040	0.030	0.50	17.00~19.00		
RESCOLOY182	ELC-18Cr -2Mo-Nb	0.015	0.40	0.40	0.035	0.025	0.50	18.50~19.30	1.80~2.30	
443	22Cr -1Cu	0.20	0.75	1.00	0.040	0.030	0.50	18.00~23.00		0.90~1.25
446	25Cr	0.20	0.75	1.50	0.040	0.030	0.50	23.00~30.00		
XM27	ULC-28Cr -1Mo	0.010	0.40	0.40	0.020	0.020	0.50	25.00~27.50	0.75~1.50	0.20 max
SHOMAC302	ULC-30Cr -2Mo	0.005	0.20	0.10	0.020	0.015	0.20	29.00~31.00	1.70~2.00	
RECLOY10	ELC-18Cr -1si-1Al-Nb	0.020	0.7~1.20	1.00	0.040	0.030		17.00~19.00		
RECLOY12	ELC-24Cr -1.5 Si-1.5Al-Nb	0.020	1.10~1.60	1.00	0.040	0.030		23.00~25.00		

Dual-Phase Stainless Steel Tubes and Pipe

Code	Material Grade	Chemical Composition (%)								
		C,max	Si,max	Mn,max	P,max	S,max	Ni	Cr	Mo	Cu
329	25Cr -4Ni-15Mo	0.08	0.75	1.00	0.040	0.030	3.00~6.00	23.00~28.00	1.00~3.00	
KES329LR	ELC-22Cr -6Ni-Ti	0.020	0.80	0.80	0.035	0.025	5.30~6.30	21.00~23.00		
RESCOLOY 195M	LC-19Cr -5Ni-2.7Mo-1.5Si	0.030	1.40~2.00	1.20~2.00	0.030	0.030	4.25~5.25	18.00~19.00	2.50~3.00	
RESCOLOY 262	ELC-21Cr -6Ni-2Mo-Ti	0.020	0.80	0.80	0.035	0.025	5.50~6.50	20.00~22.00	1.80~2.50	
KES329W	LC-22Cr -6Ni-3Mo-0.5Cu-N	0.030	1.00	1.50	0.035	0.010	4.50~6.50	21.00~23.00	2.50~3.50	0.30~0.70
KES329XM	LC-22Cr -6.5Ni-3.5Mo-0.5Cu-0.2N	0.030	1.00	2.50~3.50	0.030	0.010	6.00~7.00	21.50~22.50	3.00~4.00	0.30~0.70
KES329X	LC-22Cr -6.5Ni-3.5Mo-0.5Cu-0.15N	0.040~0.080	1.00	2.50~3.50	0.030	0.010	6.00~7.00	21.50~22.50	3.00~4.00	0.30~0.70
329J3L	LC-22Cr -5Ni-3Mo-N	0.030	1.00	1.50	0.040	0.030	4.50~6.50	21.00~24.00	2.50~3.50	
329J4L	LC-25Cr -6Ni-3Mo-N	0.030	1.00	1.50	0.040	0.030	5.50~7.50	24.00~26.00	2.50~3.50	

			Applicable Standards			Main Uses
Ti	N	Others	JIS	ASTM	DIN	
			SUS403			Heat exchangers
		Al 0.10~0.30	SUS405TB	TP405 / MT405 / UNS S40500	1.4002	
6×C-0.75			SUS409TB	TP409 / UNS S40900		
6×C-0.75			SUS409LTP SUS409LTB			
			SUS410TB SUS410TK	TP410 / MT410 / UNS S41000	1.4000 1.4006	
6×C-0.75			SUS410TiTB	UNS S40800		
			SUS430TB SUS430TK	TP430 / MT430 / UNS S43000	1.4016	
7×Cmin				TP430Ti UNS S43036	1.4510	
8×(C+N)-0.80	0.025 max.		SUS436LTP SUS436LTB			
12×C-1.10	0.04 max.	Al 0.15 max.	SUSXM8TB	TP439 UNS S43035		
	0.025 max.	Nb 8(C+N)-0.80	SUS444TP SUS444TB	18Cr-2Mo UNS S44400	1.4521(Ti) 1.4522(Nb)	Chemical reactors, heat exchangers
				TP443 / MT443 / UNS S44300		Soot blowers
	0.01-0.25			TP446 / MT446 / UNS S44600		Chemical reactors, heat-resistant protective pipe
	0.015 max.	Ni+Cu 0.50 max. Nb 0.05~0.20	SUSXM27TB	TPXM-27 UNS S44627		Heat exchangers and piping that must be resistant to crevice corrosion
	0.010 max.					
		Al 0.70~1.20 Nb+Ta 10×(C+N)-0.4			1.4742	Chemical reactors, heat exchangers, and heat-resistant protective pipe for such uses as recuperators in limestone roaster furnaces
		Al 1.20~1.70 Nb+Ta 10×(C+N)-0.4			1.4762	

			Applicable Standards			Main Uses
Ti	N	Others	JIS	ASTM	DIN	
			SUS329J1TP SUS329J1TB	TP329		Heat exchangers that must be resistant to stress corrosion cracking
5×C-0.65						Heat exchangers and piping that must be resistant to crevice corrosion
	0.05-0.10			A789 / A790 UNS S31500	1.4417	
0.20-0.40						Heat exchangers that must be resistant to stress corrosion cracking
	0.08-0.20		SUS329J4LTP SUS329J4LTB	A789 ★ A790 UNS S31803	1.4462 ★	
	0.18-0.22					
	0.10-0.20					Heat exchangers and piping that must be resistant to crevice corrosion
	0.08-0.20		SUS329J3LTP SUS329J3LTB			Tubing for deep sour well environments
	0.08-0.20		SUS329J4LTP SUS329J4LTB			

Note: Standards marked with an asterisk apply to similar, but not identical, materials.

Austenitic Stainless Steel Tubes and Pipe

Code	Material Grade	Chemical Composition (%)								
		C,max	Si,max	Mn,max	P,max	S,max	Ni	Cr	Mo	Cu
303	18Cr -9Ni-S	0.15	1.00	2.00	0.20	0.15max in	8.00~10.00	17.00~19.00		
303se	13Cr -8Ni-Se	0.15	1.00	2.00	0.20	0.060	8.00~10.00	17.00~19.00		
304	19Cr -9Ni	0.08	0.75	2.00	0.040	0.030	8.00~11.00	18.00~20.00		
304H	HC-19Cr -9Ni	0.04~0.10	0.75	2.00	0.040	0.030	8.00~11.00	18.00~20.00		
304L	LC-19Cr -11Ni	0.030	0.75	2.00	0.040	0.030	9.00~13.00	18.00~20.00		
304N	19Cr -9Ni-N	0.08	0.75	2.00	0.040	0.030	8.00~11.00	18.00~20.00		
304LN	LC-19Cr -9Ni-N	0.030	0.75	2.00	0.040	0.030	8.00~11.00	18.00~20.00		
KES304ELC	ELC-19Cr -10Ni-N	0.020	0.75	2.00	0.040	0.030	9.00~13.00	18.00~20.00		
KES304ELN	ELC-19Cr -10Ni-N	0.020	0.75	2.00	0.040	0.030	9.00~11.00	18.00~20.00		
316	17Cr -12Ni-2.5Mo	0.08	0.75	2.00	0.040	0.030	11.00~14.00	16.00~18.00	2.00~3.00	
316H	HC-17Cr -12Ni-2.5Mo	0.04~0.10	0.75	2.00	0.030	0.030	11.00~14.00	16.00~18.00	2.00~3.00	
316L	LC-17Cr -14Ni-2.5Mo	0.030	0.75	2.00	0.040	0.030	12.00~16.00	16.00~18.00	2.00~3.00	
316N	17Cr-12Ni-2.5Mo-N	0.08	0.75	2.00	0.040	0.030	11.00~14.00	16.00~18.00	2.00~3.00	
316LN	LC-17Cr-12Ni-2.5Mo-N	0.030	0.75	2.00	0.040	0.030	11.00~14.00	16.00~18.00	2.00~3.00	
KES316ELN	ELC-17Cr-13Ni-2.5Mo-N	0.020	0.75	2.00	0.040	0.030	12.00~14.00	16.00~18.00	2.00~3.00	
316B	18Cr-12Ni-2.5Mo-Ti	0.10	1.00	2.00	0.040	0.030	10.50~13.50	16.50~18.50	2.00~2.50	
316J1	18Cr-12Ni-2Mo-2Cu	0.08	1.00	2.00	0.045	0.030	10.00~14.00	17.00~19.00	1.20~2.75	1.00~2.50
316J1L	LC-18Cr-14Ni-2Mo-2Cu	0.030	1.00	2.00	0.045	0.030	12.00~16.00	17.00~19.00	1.20~2.75	1.00~2.50
317	19Cr-13Ni-3.5Mo	0.08	0.75	2.00	0.040	0.030	11.00~15.00	18.00~20.00	3.00~4.00	
317L	LC-19Cr-14Ni-3.5Mo	0.030	0.75	2.00	0.040	0.030	11.00~15.00	18.00~20.00	3.00~4.00	
321	18Cr-11Ni-Ti	0.08	0.75	2.00	0.040	0.030	9.00~13.00	17.00~19.00		
321H	HC-18Cr-11Ni-Ti	0.04~0.10	0.75	2.00	0.030	0.030	9.00~13.00	17.00~20.00		
347	18Cr-11Ni-Nb	0.08	0.75	2.00	0.040	0.030	9.00~13.00	17.00~19.00		
347H	HC-18Cr-11Ni-Nb	0.04~0.10	0.75	2.00	0.030	0.030	9.00~13.00	17.00~20.00		

			Applicable Standards			Main Uses
Ti	N	Others	JIS	ASTM	DIN	
			SUS303		1.4305	Machined parts
		Se 0.15min	SUS303Se			
			SUS304TP/SUS304TB SUS304TK/SUS304TF	TP304/MT304/ UNS S30400	1.4301	Corrosion-resistant heat exchangers, tubing, and piping
			SUS304HTP/SUS304HTB SUS304HTF	TP304H UNS S30409		Boilers and piping that must be resistant to high temperatures
			SUS304LTP SUS304LTB	TP304L/MT304L UNS S30403	1.4306	Heat exchangers and piping that require corrosion-resistant welds
	0.10-0.16		SUS304N1	TP304N UNS S30451		High-strength, corrosion-resistant heat exchangers, tubing, and piping
	0.10-0.16		SUS304LN	TP304LN UNS S30453		Boilers and piping that must be resistant to high temperatures
						Equipment that must be especially corrosion-resistant, nuclear fuel reprocessing equipment
	0.12 max.					Equipment that must be especially corrosion-resistant, nuclear plant
			SUS316TP/SUS316TB SUS316TK/SUS316TF	TP316/MT316 UNS S31600	1.4401 1.4436	Corrosion-resistant heat exchangers, tubing, and piping Nuclear fuel cladding tubes and wrapper tubes for fast breeder reactors
			SUS316HTP/SUS316HTB SUS316HTF	TP316H UNS S31609		Boilers and piping that must be resistant to high temperatures
			SUS316LTP SUS316LTB	TP316L/MT316L UNS S31603	1.4435 1.4404	Heat exchangers and piping that require corrosion-resistant welds
	0.10-0.16		SUS316N	TP316N UNS S31651		High-strength, corrosion-resistant heat exchangers, tubing, and piping
	0.10-0.16		SUS316LN	TP316LN UNS S31653		Boilers and piping that must be resistant to high temperatures
	0.12 max.				1.4429	Nuclear plant, boiler tubes, and other equipment that must possess excellent corrosion resistance and creep strength
5×C min.					1.4571	Heat exchangers and piping that must be resistant to phosphoric and sulfuric acids
			SUS316J1			
			SUS316J1L			
			SUS317TP SUS317TB	TP317/MT317 UNS S31700		
			SUS317LTP SUS317LTB	TP317L UNS S31703		
5×C min.			SUS321TP/SUS321TB SUS321TK/SUS321TF	TP321/MT321 UNS S32100	1.4541	Corrosion-resistant heat exchangers, tubing and piping
4×C-0.60			SUS321HTP/SUS321HTB SUS321HTF	TP321H UNS S32109		Boilers and piping that must be resistant to high temperatures
		Nb+Ta 10×Cmin	SUS347TP/SUS347TB SUS347TK/SUS347TF	TP347/MT347 UNS S34700	1.4550	Corrosion-resistant heat exchangers, tubing and piping
		Nb+Ta 8×C-1.00	SUS347HTP/SUS347HTB SUS347HTF	TP317H UNS S34709		Boilers and piping that must be resistant to high temperatures

Austenitic Stainless Steel Tubes and Pipe

Code	Material Grade	Chemical Composition (%)								
		C,max	Si,max	Mn,max	P,max	S,max	Ni	Cr	Mo	Cu
348	18Cr-11Ni-Nb-(Ta)	0.08	0.75	2.00	0.040	0.030	9.00~13.00	17.00~20.00		
348H	HC-18Cr-11Ni-Nb-(Ta)	0.04~0.10	0.75	2.00	0.040	0.030	9.00~13.00	17.00~20.00		
309	23Cr-14Ni	0.15	0.75	2.00	0.040	0.030	12.00~15.00	22.00~24.00		
309S	23Cr-14Ni	0.08	1.00	2.00	0.040	0.030	12.00~15.00	22.00~24.00		
310	25Cr-20Ni	0.15	0.75	2.00	0.040	0.030	19.00~22.00	24.00~26.00		
310S	25Cr-20Ni	0.08	1.50	2.00	0.040	0.030	19.00~22.00	24.00~26.00		
KES310ELC	ELC-25Cr-20Ni	0.020	0.30	2.00	0.030	0.030	19.50~21.50	23.50~25.50		
KESU1	ELC-18Cr-15Ni-2Mo	0.015	0.75	1.55~1.95	0.028	0.010	13.50~15.00	17.20~18.00	2.20~2.60	0.25 max.
KESU2	ELC-25Cr-22Ni-2Mo	0.015	0.40	1.55~1.95	0.020	0.010	21.50~22.50	24.50~25.50	2.00~2.30	0.47 max.
4449	17Cr-16Ni-5Mo	0.07	1.00	2.00	0.045	0.030	12.50~14.50	16.00~18.00	4.00~5.00	
KCP20A	20Cr-29Ni-2.5Mo-3.5Cu	0.07	1.00	2.00	0.040	0.030	24.00~38.00	19.00~21.00	2.00~5.00	1.00~4.00
KCP20B	20Cr-34Ni-2.5Mo-3.5Cu	0.07	1.00	2.00	0.045	0.035	32.00~38.00	19.00~21.00	2.00~3.00	3.00~4.00
KCP25	ELC-20Cr-25Ni-4.5Mo-Cu	0.020	1.00	2.00	0.020	0.015	24.00~26.00	19.20~20.50	4.00~5.00	1.00~2.00
KCP25A	22Cr-26Ni-5Mo-Ti	0.05	1.00	2.50	0.040	0.030	25.00~27.00	21.00~23.00	4.00~6.00	
KCP25T	21Cr-25Ni-4.5Mo-1.5Cu-Ti	0.06	0.17~1.00	1.20~2.00	0.035	0.030	24.00~26.00	20.00~22.00	4.00~5.00	1.20~1.80
KCP28T	24Cr-28Ni-3Mo-3Cu-Ti	0.06	0.80	2.00	0.045	0.030	26.00~29.00	22.00~25.00	2.50~3.50	2.5~3.5
836L	LC-20Cr-25Ni-6Mo	0.030	1.00	2.00	0.040	0.030	24.00~25.00	19.00~24.00	5.00~7.00	
KMSA1	ELC-25Cr-19Ni-3Mo-2.5Mn-0.3N	0.020	0.50	2.00~4.00	0.035	0.015	18.00~22.00	24.00~26.00	2.00~4.00	
KES825M1	20Cr-22Ni-5Mo-1.5Cu-N	0.050	1.00	3.00~4.00	0.035	0.010	22.00~24.00	20.00~21.00	5.00~6.00	1.00~2.00
KIN800AT	20Cr-33Ni-A-Ti	0.10	1.00	1.50	0.030	0.015	30.00~35.00	19.00~23.00		0.75 max.
KIN800H	HC-20Cr-33Ni-AI-Ti	0.05~0.10	1.00	1.50	0.030	0.015	30.00~35.00	19.00~23.00		0.75 max.
KIN800N	LC-20Cr-33Ni-AI-Ti	0.030	0.30~0.70	0.40~1.00	0.020	0.015	32.00~35.00	20.00~23.00		
15-5PH	15Cr-5Ni-3Cu-Nb	0.07	1.00	1.00	0.030	0.015	3.50~5.50	14.00~15.50		2.50~4.50
A286	15Cr-26Ni-2Ti-1.3Mo	0.08	1.00	2.00	0.040	0.030	24.00~27.00	13.50~16.00	1.00~1.50	

			Applicable Standards			Main Uses
Ti	N	Others	JIS	ASTM	DIN	
		Nb+Ta 10×C-1.00 Ta 0.10 max.		TP348 UNS S34800		Corrosion-resistant heat exchangers, tubing, and piping
		Nb+Ta 8×C-1.00 Ta 0.10 max.		TP348H UNS S34809		Boilers and piping that must be resistant to high temperatures
			SUS309TP SUS309TB	TP309/MT309 UNS S30900		Heat exchangers and piping that must be resistant to oxidation and corrosion at high temperatures
			SUS309STP SUS309STB	TP309S/MT309S UNS S30908		
			SUS310TP/SUS310TB SUS310TF	TP310/MT310 UNS S31000		
			SUS310STP SUS310STB	TP310S (UNS S31008) MT310S		
	0.020 max.				1.4435	Urea plants, heat exchangers and piping that must be especially resistant to corrosion
	0.10-0.14				1.4466	
					1.4449	Heat exchangers and piping that must be resistant to phosphoric and sulfuric acids
		Nb8×C min				
		Nb+Ta 8×C-1.00		B729 UNS N08020		
			SUS890LTP SUS890LTB	B677 UNS N08904	1.4539	
5×C min.				B622 UNS N08320		
5×C min.						
0.5-0.9						
	0.025 max.		SUS836LTP SUS836LTB			Heat exchangers and piping that must be resistant to chloride solution
	0.20-0.40	V 0.10-0.40		B720 UNS N08310		
	0.15-0.25			B690★ UNS N08366		
0.15-0.60		Al 0.15-0.60	NCF800TP/NCF800TB NCF800TF	B163/B407 UNS N08800		Heat exchangers and piping that must be resistant to oxidation and corrosion at high temperatures
0.15-0.60		Al 0.15-0.60	NCF800HTP/NCF800HTB NCF800HTF	B163/B407 UNS N08810		
12×C-0.60		Al 0.15-0.45/Co 0.10 max.				Heat exchangers for nuclear applications
		Nb 0.15-0.45			AMS5659	Hydraulic systems for aerospace vehicles, torque tubes
1.90-2.35		V 0.10-0.50/B0.001-0.010 Al 0.35 max.	SUH660	A453	AMS5731/AMS5732 AMS5734	Rocket engines

Note: Standards marked with an asterisk apply to similar, but not identical, materials.

Nickel and Nickel Alloy Tubes and Pipe

Code	Material Grade	Chemical Composition (%)								
		C,max	Si,max	Mn,max	P,max	S,max	Ni	Cr	Mo	Cu
KTA200	Pure Ni	0.15	0.35	0.35		0.01	99.0 min.			0.25 max.
KIN600	72Ni-15Cr	0.15	0.50	1.00	0.030	0.015	72 min.	14.00~17.00		0.50 max.
KTA825	21Cr-40Ni-3Mo-2Cu-Al, Ti	0.05	0.50	1.00	0.030	0.015	38.0~46.0	19.50~23.50	2.50~3.50	1.50~3.00
KES825M2	25Cr-40Ni-5Mo-1.5Cu-Al, Ti	0.05	1.00	2.00	0.040	0.010	40.0~42.0	24.0~26.0	5.00~6.00	1.00~2.00
KTA625	61Ni-22Cr-9Mo-Nb	0.10	0.50	0.50	0.015	0.015	58.0 min.	20.0~23.0	8.00~10.00	
KTA HB	66Ni-27Mo-5Fe	0.05	1.00	1.00	0.040	0.030	Bal.	1.00 max.	26.00~28.00	
KTA HC	60Ni-16Cr-16Mo-4W-Fe	0.08	1.00	1.00	0.040	0.030	Bal.	14.5~16.5	15.00~17.00	
KTA HX	48Ni-22Cr-9Mo-Fe, Co, W	0.05~0.15	1.00	1.00	0.040	0.030	Bal.	20.50~23.00	8.00~10.00	

Titanium and Titanium Alloy Tubes and Pipe

Material Grade	Chemical Composition (%)			
	N,max	H,max	Fe,max	O,max
KS40	0.03	0.010	0.10	0.10
KS50	0.03	0.010	0.15	0.15
KS70	0.05	0.010	0.30	0.30
KS50-Pd	0.03	0.010	0.05	0.15
KS50-Ta	0.03	0.010	0.15	0.15

16

Ti	Others	Applicable Standards			Main Uses
		JIS	ASTM	DIN	
	Fe 0.40 max.		B163 UNS N02200		Chemical plant, heat exchangers, rocket engines
	Fe 6.00~10.00	NCF600TP NCF600TB	B163/B167 UNS N06600		Heat exchangers and piping that must be resistant to oxidation and corrosion at high temperatures
0.60-1.20	Al 0.20 max.	NCF825TP NCF825TB	B423 UNS N08825		Heat exchangers and piping that must be resistant to chloride solution Tubing for deep sour well environments
0.8-1.2					
0.40 min.	Nb+Ta 3.15~4.15, Co 1.00 max. Al 0.40 max, Fe 5.00 max.		B444 UNS N06625		Chemical plant, nuclear plant that must be resistant to stress corrosion cracking
	Co 2.5 max, Fe 4.0~6.0 V 0.20~0.40		B622 UNS N10001		Chemical plant
	Co 2.5 max, Fe 4.0~7.0 V 0.35 max, W 3.00~4.00				Chemical plant, tubing for deep sour well environment
	Co 0.50~2.50, Fe 17.0~20.0 W 0.200~1.00, B 0.010 max.		B622 UNS N06002		Heat-resistant protective pipe

		Applicable Standards		Main Uses
Others	Ti	JIS	ASTM	
	remains	TTP270,TTH270	Grade 1 (B337,B338)	Chemical machinery and equipment which require corrosion resistance Urea plants Thermal, nuclear power plants heat exchangers
	remains	TTP340,TTH340	Grade 2 (B337,B338)	
	remains	TTP480,TTH480	Grade 3 (B337,B338)	
Pd 0.12~0.20	remains			Same applications as above, but with higher resistance to non-oxidizing acids
Ta 4.0~6.0	remains			

Standard Manufacturing Range

Cold finished

Hot&Cold finished

Hot finished

Outside diameter (in)	Wall thickness (mm)	Standard Manufacturing Range											
		1.0	1.2	1.6	1.8	2.0	2.3	2.6	2.9	3.0	3.5	4.0	4.5
1/2	6.0	0.125	0.143	0.715									
	8.0	0.174	0.203	0.255	0.278	0.299							
	10.0	0.224	0.263	0.335	0.368	0.399	0.441						
	12.7	0.291	0.344	0.442	0.489	0.533	0.596						
	13.8	0.319	0.377	0.486	0.538	0.588	0.659	0.725					
	15.0	0.349	0.413	0.534	0.592	0.648	0.728	0.803					
	17.3	0.406	0.481	0.626	0.695	0.762	0.859	0.952	1.040	1.069			
1	20.0	0.473	0.562	0.733	0.816	0.897	1.014	1.127	1.235	1.270			
	21.7	0.516	0.613	0.801	0.892	0.981	1.111	1.237	1.358	1.397	1.587	1.764	
	25.4	0.608	0.723	0.949	1.058	1.166	1.323	1.477	1.625	1.674	1.909	2.132	2.343
	27.2	0.653	0.777	1.020	1.139	1.255	1.427	1.593	1.755	1.808	2.066	2.312	2.545
	29.0	0.697	0.831	1.092	1.220	1.345	1.530	1.710	1.885	1.943	2.223	2.491	2.746
	30.0	0.722	0.861	1.132	1.264	1.395	1.587	1.775	1.958	2.018	2.310	2.591	2.858
	32.0	0.772	0.921	1.212	1.354	1.495	1.702	1.904	2.102	2.167	2.485	2.790	3.083
1-1/2	34.0	0.822	0.980	1.291	1.444	1.594	1.816	2.034	2.247	2.317	2.659	2.989	3.307
	38.0	0.922	1.100	1.451	1.623	1.794	2.045	2.293	2.536	2.616	3.008	3.388	3.755
	38.1	0.924	1.103	1.455	1.628	1.799	2.051	2.299	2.543	2.623	3.017	3.398	3.766
	40.0	0.971	1.160	1.530	1.713	1.893	2.160	2.422	2.680	2.765	3.182	3.587	3.979
	42.7		1.241	1.638	1.834	2.028	2.315	2.597	2.875	2.967	3.418	3.856	4.282
	45.0		1.309	1.730	1.937	2.142	2.446	2.746	3.041	3.139	3.618	4.085	4.540
	48.6		1.417	1.873	2.098	2.322	2.653	2.979	3.301	3.408	3.932	4.444	4.943
2	50.0			1.929	2.161	2.391	2.733	3.070	3.402	3.512	4.054	4.583	5.100
	50.8			1.961	2.197	2.431	2.779	3.122	3.460	3.572	4.124	4.663	5.190
	51.0			1.969	2.206	2.441	2.790	3.135	3.475	3.587	4.141	4.683	5.212
	54.0			2.088	2.341	2.591	2.962	3.329	3.691	3.811	4.403	4.982	5.549
	57.0			2.208	2.475	2.740	3.134	3.523	3.908	4.035	4.664	5.281	5.885
	60.3			2.340	2.623	2.905	3.323	3.737	4.147	4.282	4.952	5.610	6.255
	60.5			2.348	2.632	2.914	3.334	3.750	4.161	4.297	4.970	5.630	6.277
2-1/2	63.5			2.467	2.767	3.064	3.506	3.944	4.378	4.521	5.231	5.929	6.614
	65.0				2.834	3.139	3.592	4.041	4.486	4.633	5.362	6.078	6.782
	70.0				3.058	3.388	3.879	4.365	4.847	5.007	5.798	6.576	7.342
	73.0					3.537	4.051	4.560	5.064	5.231	6.059	6.875	7.679
	75.0					3.637	4.165	4.689	5.208	5.381	6.234	7.074	7.903
	76.2					3.697	4.234	4.767	5.295	5.470	6.338	7.194	8.037
	76.3					3.702	4.240	4.773	5.302	5.478	6.347	7.204	8.048
3	80.0					3.886	4.452	5.013	5.570	5.754	6.670	7.573	8.463
	82.6						4.601	5.181	5.757	5.949	6.896	7.832	8.755
	88.9						4.962	5.589	6.213	6.419	7.446	8.459	9.461
	89.1						4.973	5.602	6.227	6.434	7.463	8.479	9.483
	90.0						5.025	5.661	6.292	6.502	7.542	8.569	9.584
	100.0							6.308	7.014	7.249	8.413	9.565	10.705
	101.6							6.412	7.130	7.368	8.553	9.725	10.884
4	110.0								7.737	7.996	9.285	10.562	11.826
	114.3								8.047	8.317	9.660	10.990	12.308
	120.0										10.157	11.558	12.947
	125.0										10.593	12.056	13.507
	130.0										11.029	12.555	14.068
	135.0										11.465	13.053	14.628
	139.8										11.883	13.531	15.166
	145.0										12.337	14.049	15.749
	150.0										12.773	14.547	16.310
	155.0										13.209	15.046	16.870
	160.0										13.644	15.544	17.431
165.2										14.098	16.062	18.014	

(Unit:kg/m)

KOBE SPECIAL TUBE CO.,LTD. PLANT

Outline

1. Location

Head Office • Plant

13-1, Chofuminato-machi, Shimonoseki-City,
Yamaguchi, 752-0953 JAPAN
Tel.0832-46-3781 Fax.0832-45-1092

Sales Department Tokyo Office

9-12, Kitashinagawa, 5-chome, Shinagawa-ku,
TOKYO, 141-8688 JAPAN
Tel.03-5739-5051 Fax.03-5739-5055

Sales Department Osaka Office

Midosuji Mitsui Bldg., 1-3, Bingomachi 4-chome,
Chuo-ku, Osaka, 541-8536 JAPAN
Tel.06-6206-6305 Fax.06-6206-6471

2. Site and Building of Head Office • Plant

Site area 214,607m²
Factory area 62,705m²

3. Employees

about 400

Head Office • Plant

Tokyo Office

Osaka Office

The 1950's

- '56 Technical Agreement with CEFILAC
- '58 Hot Extrusion Shop
- '59 Cold Working Shop
- '59 Began to Operate as Chofu-Kita Plant of Kobe Steel, Ltd.

The 1960's

- '60 Use of JIS Mark on Product Approved
- '60 Authorization of Lloyd's
- '65 Authorization of TUV
- '67 Authorization of NV
- '67 Introduction of QC Activity

The 1970's

- '70 Reinforcement of Fuel Cladding Tube Shop
- '72 Technical Agreement with GE
- '73 U-Tube Inspection and Packing Shop
- '75 Long-Tubing Facilities
- '79 Award by Minister of MITI

The 1980's

- '81 New Shop for Nuclear Fuel Cladding Tube
- '82 Introduction of TQC
- '87 Precision Tube Shop
- '88 Titanium Welded Tube Shop
- '89 EP Pipe Shop
- '89 Awarded the Deming Prize

The 1990's

- '90 Introduction of TQM
- '91 Reinforcement of Nuclear Fuel Cladding Tube Shop
- '92 Authorization of ISO9002
- '94 Expanded Extrusion press Capacity
- '96 Established Kobe Special Tube

The 2000's

- '00 Zircaloy Fuel Cladding tube section separated and established Zircaloy Products Co., Ltd
- '02 Renewed as ISO9001 Company (Version 2000)

HEAD OFFICE/PLANT
13-1, Chofuminato-machi, Shimonoseki, YAMAGUCHI, 752-0953 JAPAN
Tel.(0832)46-3781 Fax.(0832)45-1092

SALES DEPARTMENT, TOKYO OFFICE
9-12, Kitashinagawa, 5-chome, Shinagawa-ku, TOKYO, 141-8688 JAPAN
Tel.(03)5739-5051 Fax.(03)5739-5055

SALES DEPARTMENT, OSAKA OFFICE
Midosuji Mitsui Bldg., 1-3, Binjomachi 4-chome, Chuo-ku, OSAKA, 541-8536 JAPAN
Tel.(06)6206-6305 Fax.(06)6206-6471